

Comtex® Technical Specifications

| | | WARP | WEFT |
|---------------------------------------|--------|-------------|-------------|
| Breaking force (per ASTM D-5034) | lbs | 268 | 340 |
| Elongation at Break (per ASTM D-5034) | % | 110 | 75 |
| Tearing strength (per ASTM D-2261) | lbs | 31 | 34 |
| Mullen Burst (per ASTM D-3786) | lbs/in | Face | 548 |
| Ball Burst (per ASTM D-3787) | lbf | Face | 418 |

| Colors | UVR% | Mean UPF | Shade factor % | SRI |
|----------------|-------------|-----------------|-----------------------|------------|
| Aquamarine | 96 | 35 | 93 | 31 |
| Aussie Green | 95 | 19 | 89 | 35 |
| Black | 96 | 40 | 96 | 1 |
| Bronze | 96 | 44 | 92 | 21 |
| Café Noir | 96 | 44 | 94 | NA |
| Cappuccino | 95 | 34 | 90 | 36 |
| Golden Yellow | 97 | 55 | 79 | 79 |
| Midnight Green | 95 | 35 | 95 | NA |
| Navy Blue | 98 | 99 | 98 | NA |
| Porcelain | 96 | 41 | 77 | 87 |
| Red | 95 | 29 | 84 | 64 |
| Rust | 95 | 27 | 90 | 33 |
| Sage | 96 | 44 | 94 | 17 |
| Sandstone | 95 | 28 | 87 | 52 |
| Silver | 94 | 17 | 94 | 18 |
| Slate Gray | 97 | 42 | 96 | NA |
| White | 90 | 27 | 75 | 96 |