



Performance Properties

Fabric Weight	9.75 oz/yd ² (330 g/m ²)
Thickness	0.44 mils
Width-Fused Edge	60 in (152 cm)
Put Up	65 yards (59 meters)
Tensile Strength ASTM D5034 (warp x fill/lbs.)	460 x 360
Mullen Burst ASTM D3786 (psi)	393
Tongue Tear ASTM D2261 (warp x fill/lbs.)	13 x 15
Taber Abrasion ASTM D3884 (cycles)	600
Hydrostatic Pressure AATCC 127 (cm)	90+
Rain Test 2 minutes/600 mm	0.00
Spray Rating AATCC 22	100
Air Permeability ASTM D737 (cfm)	0.2
Cold Crack 40°/ASTM D1912	Pass
UPF (Ultraviolet Factor)	50+
UVA & UVB (Ultraviolet Blockage)	Over 99%
Color Fastness to Light AATCC 169 option 1 (1500 hours: scale 1 - 5)	4 - 5